

BITUTHENE® Solvent Primer Vertical

Primer for use with the BITUTHENE $^{\circledR}$ range of cold applied, self adhesive waterproof membranes

Product Description

BITUTHENE® Solvent Primer Vertical is a bitumen-based primer in solvent, specially formulated to provide good initial adhesion of BITUTHENE® membranes to vertical applications, or in cold conditions.

Product Uses

Suitable for concrete with minimum grade of 25 MPa and maximum moisture content of 5%, as well as masonry or wood surfaces, on which BITUTHENE[®] membranes will be applied. BITUTHENE[®] Solvent Primer Vertical is suitable for vertical applications at -5 °C or above.

Product Advantages

- All temperature application above -5°C
- Quick drying for fast membrane application
- Rubberised formulation for high adhesion
- High surface tack prevents vertical membrane slippage
- Compatible with Bituthene sheet membrane series

Application

BITUTHENE® Solvent Primer Vertical may be applied by a roller or brush. Apply it to clean, dirt free, frost-free surfaces at a coverage rate of 5-7 m2 per litre. Allow the primer to dry 30 to 60 minutes depending on the ambient and substrate temperatures. Dry time may be longer in cold temperatures. Deep puddles of primers should be avoided as this will lengthen drying time. Do not apply directly to BITUTHENE® membrane.

In general, priming should be limited to an area that can be covered with membrane within 24 hours. Areas that accumulate significant amounts of dust or dirt must be re-primed before membrane is applied.

Health and Safety

BITUTHENE® Solvent Primer Vertical must be handled properly and stored in well ventilated place. Read the product label and Safety Data Sheet (SDS) before use. Users must comply with all risk and safety phrases. SDS's can be obtained from GCP Applied Technologies or from our web site at gcpat.com.



Key Data

PROPERTY	TYPICAL VALUE
VOC	≤600 g/L
Curing at 20°C	30 minutes

Supply

BITUTHENE® Solvent Primer Vertical	20 Litre can
Coverage	5-7 sq m per litre*
* Depending upon method of application, surface porosity and	
ambient temperature	

All declared values shown in this data sheet are based on test results determined under laboratory conditions and with the product sample taken directly from stock in its original packing without any alteration or modification of its component parts.

Release Date: 02/11/18. The information contained in this product data sheet supersedes all previous versions.

gcpat.com.au | For technical information: anz.enq@gcpat.com

Australia 1800 334 444 New Zealand 0800 552 235 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

BITUTHENE is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2019 GCP Applied Technologies, Inc. All rights reserved.

Printed in Australia GCP PDS 055 07/17

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-01-31