

EPOCOTE™ F100W Clear

General Purpose, Clear, Water-Based Epoxy Primer and Sealer

Product Description

A clear, two-pack, water-based epoxy primer and sealer with extraordinarily long-pot-life that quickly cures to a fully-bonded primer or tough, chemically resistant sealer.

Product Uses

- Primer on damp or “green” concrete substrates for BITUTHENE® LM, AQUAGARD™ polyurethane and NEWFLEX™ water-based membranes.
- Sealer to prevent efflorescence and calcium leachate staining on surface of tiles and step risers.

Features

- Very low VOC and low odour
- Long-pot-life, fast-cure, no waste
- Simple and economical application
- Easily mixed full sets, easy clean-up
- Also bonds to damp or green concrete - 10% maximum moisture content to damp or green concrete

Preparation

Substrates must be structurally sound, smooth, clean and dry. Remove all dust, laitance, loose matter, oil, curing compound, form release agents, or other contaminants.

Concrete should have a minimum strength grade of 25 MPa, and be moist-cured as required by AS 3600. Minimum age of concrete at time of waterproofing application should be 14 -28 days depending on concrete thickness and GCP primer being used.

Detailing

Detail according to NCC, and AS 4654.2 and AS 3740 requirements for external above ground and internal wet areas, respectively. Detailing should be completed before priming process starts.

Mixing

Add Part B to Part A, mix for 3 minutes using a slow speed mixer - allow to stand for 5 minutes and then re-mix.

Application

Apply undiluted EPOCOTE™ F100W Clear by brush or roller. For porous concrete substrates prone to pin holes, prime using EPOCOTE™ F100W Clear diluted 10% with clean water. Apply undiluted EPOCOTE™ F100W Clear within 24 hours as second coat.

Typical Properties

PROPERTY	TYPICAL VALUE
Mix Ratio (by wt or vol)	100:100
Solids Content (undiluted)	40%
Pot Life	60 minutes @ 25 °C
Tack Free Time (0.1mm)	2-4 hours @ 25 °C / 60% RH
Application RH	<80%
Application Temperature	10 °C to 35 °C
Maximum Re-coat Time	24 hrs @ 20 °C

NOTE

- Pot-life will reduce in hot weather. Cold weather or application onto cold surfaces will slow curing time.
- Take care to discard material that has started to get gel.

Coverage

Generally - 0.25 kg/m² (4m²/litre) dependent on substrate condition.

Packaging

EPOCOTE™ F100W–Clear

20 kg sets (approx. 20 litre)

4kg sets (approx. 4 litre)

Shelf Life

Unopened containers have 12-month shelf life from date of manufacture, when stored in a dry, cool place.

Clean-up

Generally throw-away brushes and rollers are used. Water will remove uncured product. Xylene may assist removal of gelled product.

Health and Safety

In case of spills and accidents, refer to the Material Safety Data Sheet (MSDS) of the products or when in doubt contact your local GCP representative. Always wear protective clothing, gloves and protective goggles when handling chemical products. For full information, consult the relevant MSDS.

Limitations

Information contained in this document does not cover all possible application scenarios or imply product suitability for an application. Please contact your local GCP representative or the GCP Technical Department for further information.

Warranties

GCP and contractors recognised by GCP as experienced in the application of GCP products will provide warranties for individual projects. Warranty periods offered are dependent on project details and complexity. Requests for very long warranty periods may necessitate increased membrane thicknesses to ensure longevity. Contact your local GCP representative for further details.

Release Date: 02/11/18. The information contained in this product data sheet supersedes all previous versions.

gcpat.com.au | Australia customer service: 1800 855 525

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

AQUAGARD, BITUTHENE, EPOCOTE, NEWFLEX and SILCOR are trademarks of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2021 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebald Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-01-31

gcpat.com.au/solutions/products/epocote-f100w-clear